

## Colors

Color Name	Solar Reflective Color	Aluminum		Steel	
		Reflectivity	Emissivity	Reflectivity	Emissivity
Almond	SR	0.61	0.88	0.57	0.89
Award Blue		0.19	0.88	0.16	0.88
Bone White	SR	0.72	0.89	0.68	0.89
Brandywine **	SR	0.25	0.87	0.24	0.90
Champagne Metallic	SR	0.40	0.82	0.37	0.82
Charcoal Gray	SR	0.26	0.87	0.26	0.87
Cityscape	SR	0.36	0.89	0.35	0.89
Classic Copper	SR	0.49	0.82	0.41	0.82
Colonial Red	SR	0.32	0.87	0.32	0.87
Dark Bronze *	SR	0.07	0.91	0.26	0.88
Dark Ivy **	SR	0.26	0.88	0.24	0.86
Electric Blue		0.21	0.88	0.21	0.88
Extra Dark Bronze		0.06	0.88	0.06	0.90
Hartford Green		0.09	0.88	0.09	0.91
Hemlock Green	SR	0.32	0.88	0.32	0.88
Mansard Brown	SR	0.26	0.87	0.26	0.87
Matte Black *	SR	0.05	0.90	0.26	0.89
Medium Bronze	SR	0.27	0.88	0.27	0.88
Patina Green	SR	0.27	0.90	0.26	0.90
Regal Blue		0.15	0.88	0.15	0.89
Regal Red	SR	0.52	0.87	0.44	0.89
Sandstone	SR	0.52	0.89	0.49	0.89
Sherwood Green	SR	0.26	0.89	0.26	0.89
Sierra Tan	SR	0.36	0.90	0.35	0.89
Silver Metallic	SR	0.60	0.78	0.60	0.78
Sky Blue	SR	0.27	0.88	0.27	0.88
Slate Gray	SR	0.34	0.88	0.34	0.88
Stone White	SR	0.63	0.89	0.58	0.89
Teal		0.13	0.90	0.13	0.89
Terra Cotta	SR	0.39	0.90	0.35	0.90
Tropical Patina	SR	0.28	0.88	0.28	0.88
Hunter Green (custom)	SR	0.26	0.87	0.26	0.87
Pacific Blue (custom)	SR	0.26	0.88	0.26	0.88
Spruce (custom)	SR	0.30	0.88	0.30	0.88

\* Steel Only SR  
 \*\* Aluminum Only SR

Reflectivity is the materials ability to deflect the heat energy of the sun  
 Emissivity is the materials ability to release the heat energy of the sun